

General Description

Junckers BASEFILL is a quick-drying fillerbase, which, in combination with Junckers solvent-based or water-based lacquers, is suitable for most sanded and untreated parquet floors, including most exotic wood floors.

Junckers BASEFILL is to be mixed with sanding dust from the floor sanding process.

Junckers BASEFILL should be used only as a filler-base.

Technical Data

Product:	Solventborne filler-base to be mixed with wood powder from sanding of the actual floor.
Package sizes:	5 litre, 10 litre and 12 litre.
Appearance:	Colourless.
Coverage:	10 m ² per litre.
Application tools:	Broad full-edged spatula of stainless steel.
Substrate temperature:	Minimum 10°C.
Dilution:	Delivered ready for use. Dilution is not recommended.
Drying time:	Dry to touch after approx. 15 min. at 20°C and 50 %RH.
Cleaning of tools:	Junckers Thinner 007.
Storage:	Lasts for 2 years if unopened and stored at 20°C.

System Recommendations

High traffic areas:	1 coat Junckers BASEFILL 10 m ² /ltr.
	+ 2 coats Junckers High Performance Commercial 10m ² ltr.
	or
	1 coat Junckers BASEFILL 10 m ² /ltr
	+ 2 coats Junckers ISOLAK 10 m ² /ltr
	or
	1 coat Junckers BASEFILL 10 m ² /ltr
	+ 2 coats Junckers STRONG 10 m ² /ltr
Low traffic areas:	1 coat Junckers BASEFILL 10 m ² /ltr
	+ 1 coat Junckers PRO TECH 10 m ² /ltr
	or
	1 coat Junckers BASEFILL 10 m ² /ltr
	+ 1 coat Junckers PRO FINISH 10 m ² /ltr
Sport areas:	1 coat Junckers BASEFILL 10 m ² /ltr.
	+ 2 coats Junckers HP SPORT 10m ² ltr
	or
	1 coat Junckers BASEFILL 10 m ² /ltr
	+ 2-3 coats Junckers ISOLAK 10 m ² /ltr

Directions for Use

Untreated/sanded floors

Ensure that the surface is absolutely clean, dry and free from all dust, wax, grease, polish, soap residues etc. Sand the surface to remove dirt and irregularities. Vacuum thoroughly and mix enough sanding dust into **Junckers BASEFILL** until a thick but spreadable paste is obtained. If too thick adjust with **Junckers BASEFILL**. Spread the paste quickly using a stainless steel spatula. Sand with sandpaper grit 120-150. Vacuum thoroughly. Proceed according to “**System recommendations**”.

Previously lacquered floors:

Use grit 24-36 to strip old coats. Then remove abrasion marks with grit 60-80. Finally, use grit 100-120 to obtain a completely smooth surface. Vacuum sanding dust and prime the floor as described under “**Untreated/ sanded floors**”.

Important!

Before use of the product, read the label on the container carefully and observe the advised precautionary safety measures.

Important!

Stir well before use.

Further information

Products:

- F 4.2 - **Junckers PRO FINISH**
- F 5.1 - **Junckers STRONG**
- F 6.2 - **Junckers PRO TECH**
- F 7.1 - **Junckers ISOLAK**
- F 7.5 - **Junckers THINNER 007**
- F 8.2 - **Junckers HP SPORT**
- F 8.5 - **Junckers High Performance Commercial**