

General Description

Junckers Professional Hardwax Oil is suitable for sanded and untreated parquet floors.

Junckers Professional Hardwax Oil protects the floor and gives the floor a light warm appearance.

Junckers Professional Hardwax Oil is used for both priming and finishing. Certain porous timbers may require additional coats to achieved desired result.

Technical Data

Product:	Hard wax and drying oil in solvents.
Package sizes:	2.5 and 5 litres.
Appearance:	Haze light brown liquid. Dries up to a clear film.
Gloss level:	Matt to Satin.
Coverage:	20-30 m ² per litre.
Application tools:	Stainless steel spatula, roller or brush. According to gloss a white or red pad for polishing.
Substrate temperature:	Minimum 10°C.
Dilution:	Delivered ready for use.
Drying time:	Dry to touch approx. 4 hours at 20°C. Recoating approx. 6 hours at 20°C. Buffing approx. 16 hours at 20°C. Full cure after 6 days at 20°C.
Cleaning of tools:	Junckers Thinner 007.
Storage:	Lasts for 2 years if unopened and stored at 20°C. Once opened the product will start to form a skin and may harden in the can.

System Recommendations

- High traffic areas:** 2 coats **Professional Hardwax Oil** 20 m²/ltr.
+ 1 polishing coat **Professional Hardwax Oil** 50 m²/ltr.
- Low traffic areas:** 1 coat **Professional Hardwax Oil** 20 m²/ltr.
+ 1 polishing coat **Professional Hardwax Oil** 50 m²/ltr.

Directions for Use

Untreated/sanded floors

The surface should be clean, dry and free from dust, wax, grease, polish etc. Machine sand the floor as advised under **Previously treated floors** to remove dirt and irregularities. The last sanding should be carried out by using minimum grit 120 sandscreen mesh before applying **Junckers Professional Hardwax Oil**. Thoroughly clean off the sanding dust (e.g. by vacuuming).

Apply **Junckers Professional Hardwax Oil** using suitable tools. Allow to penetrate then remove surplus material using buffing machine and soft cloth or pad. When dry apply subsequent coats as described.

To improve gloss, buff using white pad after a minimum 16 hours.

Previously treated floors:

Machine sand using grit 24-36. Remove abrasion marks with grit 60-80. Finally, use grit 100-120 to obtain a completely smooth surface. Vacuum sanding dust and prime the floor as described under “**Untreated/ sanded floors**”.

Cleaning:

Add **Junckers Sylva Cleaner** to the cleaning water.

Maintenance:

Use **Junckers RUSTIC TOP OIL** for refreshing of the surface. For worn surfaces use **Junckers Professional Hardwax Oil** to restore the surface protection.

Important!

Wait until full cure before replacing rugs or carpets.

Important!

Before use of the product, read the label on the container carefully and observe the advised precautionary safety measures.

Important!

Stir well before use.

Further information

Products:

- F 2.5 - **Junckers Thinner 008**
F 2.7 - **Junckers RUSTIC TOP OIL**
F 7.5 - **Junckers Thinner 007**
F 10.2 - **Junckers Sylva Cleaner**